

# American National Standard for video recording – 1-in magnetic recording tape

Approved January 9, 1989

Sponsor: Society of Motion Picture and Television Engineers

## 1. Scope

This standard specifies the dimensions of 1-in video magnetic recording tape, and the direction of magnetic orientation.

## 2. Dimensions

The dimensions of the magnetic tape shall be as specified below when the tape is normalized at 23°C ± 1°C and 50 ± 2 percent relative humidity:

| Dimensions                | Millimeters    |
|---------------------------|----------------|
| Width                     | 25.350 ± 0.025 |
| Maximum overall thickness | 0.030          |

## 3. Direction of Orientation

The direction of orientation of the magnetic coating shall be longitudinal.

# American National Standard for video recording – 1-in helical-scan recorders – raw stock for reference tapes

Approved January 9, 1989

Sponsor: Society of Motion Picture and Television Engineers

## 1. Scope

This standard specifies dimensions for the width, thickness, and width deviation of raw tape stock used to record reference tapes for 1-in helical-scan video tape recorders. Conditions before testing and testing environment are also specified.

## 2. Referenced American National Standard

This standard is intended for use in conjunction with the following American National Standard:

ANSI/ASTM D638M-87, Test Method for Tensile Properties of Plastics

## 3. Conditioning for Testing and Recording

3.1 Tests, measurements, and recordings made on the raw tape stock to check the requirements of this standard shall be made under the following conditions:

|                     |                |
|---------------------|----------------|
| Temperature         | 23°C ± 1°C     |
| Relative humidity   | 50 ± 2 percent |
| Barometric pressure | 86 to 106 kPa  |

3.2 The raw tape stock shall be stabilized at the above conditions for 24 hours, rewound on a reel at a tape tension of 2.0 N ± 0.5 N, and kept at the same conditions for another 24 hours.

## 4. Dimensions

4.1 Tape Stock. The dimensions of the tape stock

for recording reference tapes shall be as specified below:

|                              |                                      |
|------------------------------|--------------------------------------|
| Dimensions                   | Millimeters                          |
| Width                        | 25.350 ± 0.025                       |
| Thickness                    | 0.027 to 0.030                       |
| Maximum rate of width change | less than 0.015 over a length of 250 |

4.2 Longitudinal Dimensional Change. The longitudinal dimensional change of the raw tape stock kept under the following conditions for 48 hours shall be less than 0.03 percent:

|                   |                |
|-------------------|----------------|
| Temperature       | 45°C ± 1°C     |
| Relative humidity | 85 ± 2 percent |
| Tape tension      | 2.0 N ± 0.5 N  |

The longitudinal dimensional change shall then be measured after storage for 24 hours under the conditions specified in Sec. 3.1.

4.3 Modulus of Elasticity. The longitudinal modulus of elasticity shall be measured in accordance with ANSI/ASTM D638M-87, and shall meet the following specifications:


|         |                       |                        |
|---------|-----------------------|------------------------|
|         | N/mm <sup>2</sup>     | lb/in <sup>2</sup>     |
| Minimum | 2.9 x 10 <sup>8</sup> | 0.43 x 10 <sup>8</sup> |
| Maximum | 7.4 x 10 <sup>8</sup> | 1.07 x 10 <sup>8</sup> |

4.4 Poisson's Ratio. Poisson's ratio shall be 0.4 nominal.

NOTE: In addition to the parameters specified in this standard, there are other parameters such as coating and frictional characteristics that affect the operation of the tape. Manufacturers of reference tapes should take these parameters into consideration.


CAUTION NOTICE: This American National Standard may be revised or withdrawn at any time. The procedures of the American National Standards Institute require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute. Printed in USA

Copyright © 1989 by the Society of Motion Picture and Television Engineers. Reprinted by permission.

 American National Standards Institute, 1430 Broadway, New York, N.Y. 10018

CAUTION NOTICE: This American National Standard may be revised or withdrawn at any time. The procedures of the American National Standards Institute require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute. Printed in USA

Copyright © 1989 by the Society of Motion Picture and Television Engineers. Reprinted by permission.

 American National Standards Institute, 1430 Broadway, New York, N.Y. 10018